


Registered trademark	PVC Resin	Properties							Application
		K-Value	Degree of Polymerization	Bulk Density (g/ml)	Volatile Matter (%)	Residual VCM (ppm)	Average Particle Size (μm)	DEHP Absorption (ml/g)	
大洋塑膠粉 YEEVINYL®  POLYVINYL CHLORIDE RESIN 聚氯乙烯粉	S-101 (SG5)	66±1	1030±50	0.56±0.05	<0.5	<1.0	125±30	>0.20	General rigid sheets and pipe, good for rigid or flexible product
	S-103 (SG3)	70±1	1250±50	0.53±0.05	<0.5	<1.0	120±30	>0.25	Insulating materials, vinyl tape, PVC sheets and leather, good for high quality of flexible or semi-rigid product
	S-107 (SG8)	57±1	700±50	0.60±0.05	<0.5	<1.0	125±30	>0.10	Blowing bottles, good liquidity for rigid and high transparency product
	S-108 (SG7)	60±1	770±50	0.60±0.05	<0.5	<1.0	130±30	>0.15	Vinyl tape, IC tube, good for rigid and high transparency product