



产品介绍 PRODUCTS INTRODUCTION

■ 聚氯乙烯树脂(GRADE DG-1300) PVC RESIN DG-1300

ITEMS 项目	SPECIFICATIONS 规格	PACKING 包装
Average polymerization degree: Impurity particle number/100g Volatile matter Bulk density g/ml 0.35mm mesh residue Fish eyes number/100cm ² Initial whiteness Whiteness(160°C, 10min) VCM residuals ug/g K Value	1300+/-80 50 max 0.3% max 0.50+/-0.04 0.1% max 5 max 90% min 78% min 1 max 71-72	Packing in 25kg PP/ kraft paper bag or in jumbo bag
平均聚合度: 杂质粒子数, 个/100g ≤ 挥发物 ≤ 表面密度 g/ml: 0.35mm筛余物 ≤ 鱼眼数 个/100cm ² ≤ 原始白度 ≥ 白度 (160°C, 10min) ≥ VCM残留ug/g ≤ K值	1300+/-80 50 0.3% 0.50+/-0.04 0.1% 5 90% 78% 1 71-72	25公斤复合牛皮纸袋或吨袋

■ 聚氯乙烯树脂(GRADE DG-1000K) PVC RESIN DG-1000K

ITEMS 项目	SPECIFICATIONS 规格	PACKING 包装
Average polymerization degree: Impurity particle number/100g Volatile matter Bulk density g/ml 0.35mm mesh residue Fish eyes number/100cm ² Initial whiteness Whiteness(160°C, 10min) VCM residuals ug/g K Value	1030+/-50 50 max 0.3% max 0.53+/-0.03 0.1% max 5 max 90% min 78% min 1 max 66 - 68	Packing in 25kg PP/ kraft paper bag or in jumbo bag
平均聚合度: 杂质粒子数, 个/100g ≤ 挥发物 ≤ 表面密度 g/ml: 0.35mm筛余物 ≤ 鱼眼数 个/100cm ² ≤ 原始白度 ≥ 白度 (160°C, 10min) ≥ VCM残留ug/g ≤ K值	1030+/-50 50 0.3% 0.53+/-0.03 0.1% 5 90% 78% 1 66 - 68	25公斤复合牛皮纸袋或吨袋